- denterline -

SST-A0082

PRACTICAL COLD SPRAY COATINGS

TECHNICAL DATA SHEET

Document No: SST-TDS-A0082-PR-2.0-0120 Release Date: January 2020



Commercial Powder

Metal Group – **ALUMINUM** Catalogue No. – **SST-A0082**



Description:

A general purpose aluminum-based blend of aluminum and high purity alumina particles with good deposition growth rate, smooth surface and high bonding strength on Mg and Al alloys. The blend particle size distribution is specially tailored for the cold spray process, suitable for repairing a variety of aluminum and magnesium parts. The coating presents full density, excellent bonding strength, excellent machinability and excellent corrosion resistance.

Specifications:

Material Properties

Composition: Al 99.5% Min., Al₂O₃ 99.0% Min.

Particle Size: -75 to +5 µm


Characteristics: Irregular shaped particles for


maximum velocity


Typical Coating Properties

Bond Strength*:> 6000 psi> 7500 psiHardness (Brinell):57 - 6260 - 63Density:> 99.5%> 99.5%Deposition Efficiency:Up to 20%Up to 40%Deposition Rate:Up to 5 g/minUp to 30 g/min

Typical Micrograph







SST-A0082 Coating on Al6061 (Series EP)

Spray Parameter Ranges

Spray parameters only apply to CenterLine Cold Spray equipment.

Series P/PX	Series EP/EP

Temperature: 300 - 500°C 300 - 550°C

Pressure: 100 - 250 psi 100 - 500 psi

Powder Pre-heating: N/A N/A

Standoff Distance: 10 – 25 mm 10 – 40 mm

Gas: Compressed air or Nitrogen

Feed Rate (gram/min): 12 – 25 12 – 80

Gun Traverse Speed: 10 – 500 mm/s depending on

process settings and target

coating thickness

Surface Preparation: SST-G0002 commercial blast

Spray Nozzle: UltiLife™

Ordering

Catalogue Number: SST-A0082

Standard Packaging: 400 ml or 1 gallon sized container

Selling Unit: Pound

Material Certification: Available upon request

To discuss your Cold Spray Application(s), including the optimization of spray parameters for higher coating bond strengths, or for more information about powders and blends, please contact your CenterLine SST representative or visit our website at www.supersonicspray.com.

^{*}Higher bond strengths can be achieved. Please consult with CenterLine to receive assistance in optimizing the spray parameters.